

# FLOORCO TRADING LTD.

## TEST REPORT

**SCOPE OF WORK**

SPC FLOORING

**REPORT NUMBER**

230804003SHF-004

**TEST DATE(S)**

2023-08-04 - 2023-08-15

**ISSUE DATE**

2023-09-04

**PAGES**

5

**DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10k(September 1, 2022)

© 2022 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



## Test Report

### Statement

- 1.This report is invalid without company's special seal for testing on the assigned page.
- 2.This report is invalid without an authorized person's signature.
- 3.This report is invalid if altered.
- 4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
- 7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
- 8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
- 9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



## Test Report

Issue Date: 2023-09-04 Intertek Report No. 230804003SHF-004  
Applicant: FLOORCO TRADING LTD.  
Address: 118 CARBINE ROAD, MT WELLINGTON  
Attn: Terry SHI  
Test Type: Performance test, samples provided by the applicant.

### Product Information

Product Name	SPC FLOORING	Brand	/
Sample Description	Good Condition	Sample Amount	10pcs
		Received Date	2023-08-01
Sample ID	Model	Specification	
S230804003SHF.001	ATWOOD 5.7MM	/	

### Test Methods And Standards

Test Standard	EN 438-2:2016+A1:2018, Section 25
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

#### Note:

- 1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.
- 2.Test results were cited from Intertek Report No. 230804003SHF-001

### Report Authorized

  
*Sally Xie*      *Daniel Zhang*  
Name: Sally Xie      Daniel Zhang  
Title: Reviewer      Project Engineer



# Test Report

Issue Date: 2023-09-04

Intertek Report No. 230804003SHF-004

**Test Items, Method and Results:**

Test Item: Resistance to scratching

Test Method: EN 438-2:2016+A1:2018, Section 25

Conditioning: Condition the test specimens at (23±2)°C and (50±5)% relative humidity for at least 72h

Test Result:

Parameter	Specimen 1	Specimen 2	Specimen 3
Rating scale	Rating 3	Rating 3	Rating 3

Scratch resistance rating scale

	Discontinuous scratches, or faint superficial marks, or no visible marks.	≥ 90 % continuous double circle of scratch marks clearly visible.
Rating 5	6 N	> 6 N
Rating 4	4 N	6 N
Rating 3	2 N	4 N
Rating 2	1 N	2 N
Rating 1	-	1 N




## Test Report

Issue Date: 2023-09-04

Intertek Report No. 230804003SHF-004

### Appendix A: Sample Received Photo



### Revision:

NO.	Date	Changes
230804003SHF-004	2023-09-04	First issue