



## No. 1398435.6AR1

(Please quote this number in all correspondence)

CLIENT:

SAMPLE RECEIVED FROM:

SAMPLE DESCRIPTION:

Date Received: 17.11.21

Floorco Trading Ltd. 38 Galway St.

Floorco

Iway St

Onehunga, Auckland

Flooring planks: "The Laminate Flooring".

Attn.: Henry Zhai

Client Order No.:

Client Reference:

1 of 1

## ISO 20251:2016(E) - TEXTILE FLOOR COVERINGS - WATER IMPERMEABILITY TEST

**Principle** – a specified amount of coloured liquid is poured onto a textile floorcovering, where it is contained in a concentrated area for 24 hours. The floor covering is evaluated for liquid penetration through the product.

- 1. 3 samples are taken, each at least 350 x 350 mm.
- 2. The samples are conditioned and tested at 20°C and 65% RH.
- 3. Each sample is placed on top of clean white tissue paper, with the use surface uppermost.
- 4. A PVC cylinder 85 mm diameter (modified from 110 mm) is placed in the centre of each carpet.
- 5. 100 ml of coloured liquid (water and dye) is poured into the centre of each cylinder.
- 6. After 24 hours the white tissue is examined for evidence of water penetration though the backing.

Result:

Water Impermeability

Note: The samples were tested on the joints along its long side.

This report is reissue. Extra information regarding the methodology has been added.

L A Greer Signatory C Judan Signatory

21/03/2023